



# 467MP Transfer Tape

## Product Data Sheet

Updated : April 2004  
Supersedes : November 2001

### Product Description

A-30 is a firm acrylic pressure-sensitive adhesive system. It features high ultimate bond strength with excellent high temperature performance and excellent

solvent resistance. Bond strength increases substantially with natural ageing.

467 is a long ageing resistant product used extensively by the nameplate industry.

### Physical Properties

Not for specification purposes

<b>Adhesive Type</b>	Firm Acrylic	<b>3M ref</b> : A-30
<b>Thickness</b> (ASTM D-3652) Tape Liner Total	50 µm      2 Thou 100 µm 150 µm	
<b>Release Liner</b>	Tan printed polycoated paper.	
<b>Tape Colour</b>	Clear	
<b>Shelf Life</b>	24 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

### Performance

#### Characteristics

Not for specification purposes

<b>Adhesion to Stainless Steel</b> ASTM D-3330	5.5 N/10mm	
<b>Shear Resistance</b>	High	
<b>Temperature Performance</b> Max : Minutes / Hours Max : Days / Weeks Minimum	204 °C 149 °C -30 °C	
<b>Solvent Resistance</b>	Excellent. When the adhesive is properly applied to impervious materials, it will resist solvent attack and adhesive softening through edge contact with mild acids and alkalines, oils, grease, gasoline kerosene, JP-4 fuel, and many other standard aromatic and aliphatic solvents. However, it is not recommended for uses where continuous immersion is required.	

Date : April 2004  
467MP Transfer Tape

<b>Performance Characteristics (Cont..)</b> Not for specification purposes	<b>UV Light Resistance</b>	Excellent. Will not oxidise when exposed to air or sunlight UV.
	<b>Water Resistance</b>	Excellent. There are no evident adverse effects on the bond of properly applied materials after immersion in 21°C water for about 100 hours.

<b>Additional Product Information</b>	The legend Hi Performance No. 467 is imprinted on the release liner.	467MP is designed with a moisture resistant release liner which resists cockling or wrinkling from high humidity.  The 50 micron thick adhesive is ideally suited for	joining materials that are relatively smooth, thin and have low residual stress. If rough or thick materials with a small degree of residual stress are to be joined, then the 130 micron thick adhesive should be considered
---------------------------------------	--	---	---

<b>Application Techniques</b>	<p>1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact &amp; thus improves bond strength.</p> <p>2. To obtain optimum adhesion, the bonding</p>	<p>surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol &amp; water. Use proper safety precautions for handling solvents.</p> <p>3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F).</p>	Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.
-------------------------------	--	---	---

<b>Applications</b>	467MP is well suited for bonding together a wide variety of similar and dissimilar materials such as metals, paints, wood, glass and some plastics.	<p>An excellent adhesive for mounting nameplates and decorative trim.</p> <p>Automotive Industry.</p>
---------------------	---	---

<b>Specifications</b>	This tape meets the requirements of U.S. Government specification MIL-P-19834, Amendment 1, Type 1.	467MP is a UL and AGA recognised product.
-----------------------	---	---

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



#### Tapes & Adhesives Group

© 3M United Kingdom PLC 2004

3M United Kingdom PLC  
3M Centre  
Cain Road  
Bracknell, Berkshire,  
RG12 8HT

Product Information :  
  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
  
Tel (01) 280 3555  
Fax (01) 280 3509