



Membrane Switch Spacer 7959MP

Product Data Sheet

Updated : April 2004
Supersedes : July 2000

Physical Properties

Not for specification purposes

Liner	0.10mm 58# Polycoated Kraft
Adhesive	0.05mm #200 "High Performance" Acrylic
Carrier	0.127mm Polyester Film
Adhesive	0.05mm #200 "High Performance" Acrylic
Liner	0.10mm 58# Polycoated Kraft
Shelf Life	12 months from date of manufacture by 3M if stored at room temperature condition in cool, dry and sun protected room.

Features:

- Long term, environmentally stable bond
- High cohesive strength to withstand repeated stresses from switch activation.
- Excellent temperature, humidity, and chemical resistance.
- High bond strength to high surface energy plastics such as polyester and polycarbonate.

Applications

- Spacer for membrane switch/keyboard circuits.

Date : April 2004
 Membrane Switch Spacer
 7959MP

Properties and Performance
 Not for specification purposes

Temperature Range	Low : -40°F (-40C) High Long Term (days/weeks) : 250°F (121°C). High Short Term (minutes/hours) : 300°F (149°C).
Chemical Resistance	Solvent resistance is excellent when this product is properly applied to impervious materials. The adhesive resists softening through edge contact with mild acids, alkalis, oil, gasoline, Kerosene, JP-4 fuel and many other solvents. Not recommended for total immersion.
Dielectric Strength (ASTM D149)	1.6 KV/mil
Insulation Resistance (ASTM P257)	1.1×10^{14} ohms
Volume Resistivity (ASTM D257)	1.1×10^{15} ohm-cm
Surface Resistivity (ASTM D257)	3.4×10^{14} ohms/square
Moisture & Humidity Resistance	No adverse effect on the bond after exposure to 100% Relative Humidity at 100°F.
Bond Build Up	The bond strength of Scotch #200 Hi-Performance Acrylic adhesive increases as a function of time and temperature.
U.V. Resistance	Adhesive is very resistant to oxidation and ozone when exposed to air or sunlight (U.V.).

Physical Properties
 Not for specification purposes

180° Peel 12"/minute 1 mil polyester to stainless steel (ASTM D903)
10.2 N/10mm

3M test 90° peel 12"/minute 8 mil aluminium to various surfaces		
	72 hour Dwell N/10mm	Ultimate Bond N/10mm
Stainless Steel	11.2	7.8
Epoxy	11.4	9.6
Polyester	9.4	10.2
Polycarbonate	10.6	13.4
ABS	14.4	10.4

Date : April 2004
 Membrane Switch Spacer
 7959MP

Application Techniques

- Bond strength is dependent upon the amount of adhesive surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.
- To obtain optimum adhesion, the bonding surfaces must be clean, dry and smooth. Some typical surface cleaning solvents are isopropyl alcohol or heptane. Use proper safety precautions for handling solvents.
- Ideal tape application temperature range is 70°F to 100°F.
- Application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Tapes & Adhesives Group

3M United Kingdom PLC
 3M Centre
 Cain Road,
 Bracknell, Berkshire,
 RG12 8HT

Product Information :
 Tel 0870 60 800 50
 Fax 0870 60 700 99

3M Ireland
 3M House, Adelphi Centre,
 Upper Georges Street,
 Dun Laoghaire, Co. Dublin,
 Ireland

Customer Service :
 Tel (01) 280 3555
 Fax (01) 280 3509

© 3M United Kingdom PLC 2004