

# LEXAN<sup>\*</sup> 8B36V Film

## Product Datasheet

### DESCRIPTION

LEXAN<sup>\*</sup> 8B36V is a one side suede, one side matt transparent polycarbonate film for applications which require UL94 flammability performance. It offers high temperature resistance, excellent dimensional stability, and good printability without pre- treatment making it very suitable for multi-layer printing. The heavy suede texture offers mar resistance and the product can be used over light-emitting devices. Its low gloss level reduces glare in automobile interiors and offices.

### Typical Property Values<sup>1</sup>

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
<b>Mechanical</b>						
Tensile Strength						
@ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2506
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100-154
Gardner Impact Strength at 0.03 in. (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propogation	ASTM D1922	g/mil	30-55		g/mil	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010 inch (0.25 mm)	ASTM D2176-69	double folds	60			
0.020 inch (0.50 mm)	ASTM D2176-69	double folds	20			
<b>Thermal</b>						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft <sup>2</sup> /°F/in	1.35		W/m <sup>2</sup> K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x 10 <sup>-5</sup> /°F)	3.2	ISO 11359	(x 10 <sup>-5</sup> /°C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417/D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	312		°C	156
Heat Deflection Temp. by TMA at 1.8 MPa		°F	350	ISO 75 Modified	°C	175
Shrinkage at 302 °F (150 °C)	ASTM D1204	%	1.40%		%	1.40%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

### UL Flammability Rating / Performance Levels

Thickness	Rating
> 0.010" (0.250 mm) and < 0.015" (0.375 mm)	UL94V-2
0.015" (0.375 mm) and greater	UL94V-2
File Number	E61257

### Manufacturing Specifications

Nominal Gauge Ranges	Min./Max of
0.010-0.015" (0.250-0.375 mm)	± 5%
0.020" (0.500 mm)	± 3%

1 These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Advanced Materials, Specialty Film & Sheet representative or the GE Advanced Materials, Specialty Film & Sheet Quality Services Department. Reported values are based on 0.010" (0.250 mm) thickness unless otherwise noted.

\* LEXAN is a trademark of General Electric Company.



# GE Advanced Materials Specialty Film & Sheet

Property	ASTM Test Method	Units	Value	ISO Test Method	Units	Value
<b>Physical</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	75	ISO 1183	kg/m <sup>3</sup>	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Roughness (RMS)	ASME B46-1	-	see chart			
Surface Energy (1st surface / 2nd surface)	ASTM D5946-01	-	38/32			
Surface Tension (1st surface / 2nd surface)	Dyne Pens	Dyne	>44 / >44			
<b>Optical</b>						
Refractive Index @ 77 °F (25 °C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	85			
Yellowness Index	ASTM D1925	%	2			
Haze	ASTM D1003	%	102			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	4	ISO 2813	-	4

## Gloss: (ASTMD 523-60)

8B36V	Angle		Suede	Matte
	60°	Minimum	0	3
	Maximum	2	12	

Europe:  
GE Advanced Materials  
Specialty Film & Sheet  
Plasticslaan 1  
PO Box 112  
NL - 4600 AC Bergen op Zoom  
The Netherlands  
Tel. +31 (164) 292742  
Fax. +31 (164) 291986

Americas:  
GE Advanced Materials  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. +1 (413) 448 7110  
Fax. +1 (413) 448 7506

Pacific:  
GE Advanced Materials  
Specialty Film & Sheet  
1266 Nanjing Road (W)  
16th Floor, Plaza 66  
200040 Shanghai  
China  
Tel. +86 21 6288 1088  
Fax. +86 21 6288 0818

For more information call: (800) 451-3147

Visit us online at: [www.geadvancedmaterials.com](http://www.geadvancedmaterials.com)

©2005 General Electric Company  
All Rights Reserved

**DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE GE ADVANCED MATERIALS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE ADVANCED MATERIALS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GE ADVANCED MATERIALS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, GE ADVANCED MATERIALS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of GE Advanced Materials' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE Advanced Materials' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE Advanced Materials' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE Advanced Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\* LEXAN is a trademark of General Electric Company.

