

Lexan^{*} FR25A Film

Product Datasheet

DESCRIPTION

Lexan[®] FR25A flame-retardant film is an opaque, thin-gauge polycarbonate film with a velvet finish on one side and a polish finish on the other, and a UL94 V-0 listing to meet the stringent requirements in a wide range of electrical, electronic and transportation applications. Lexan FR25A Film offers improved score and bend fabrication capability versus Lexan FR700 in addition to ease of thermoforming, hydroforming, embossing, die-cutting, folding and bending. It is suitable for applications such as printed circuit board insulation, backlit aircraft in-flight panels and displays, business equipment insulation, computer rack partitions, and TV and monitor insulation. Standard available colors include black, white, light grey and dark grey.

Typical Property Values¹

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength						
@ Yield	ASTM D882	psi	10000	ISO 527	MPa	70
Ultimate	ASTM D882	psi	8700	ISO 527	MPa	60
Tensile Modulus	ASTM D882	psi	319000	ISO 527	MPa	2200
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100-155
Gardner Impact Strength at 0.03 in. (0.75 mm)	ASTM D3029	ft-lb	21	ISO 6603-1	J	28
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	298
Propagation	ASTM D1922	g/mil	30-55		kN/m	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010 inch (0.25 mm)	ASTM D2176-69	double folds	45			
0.020 inch (0.50 mm)	ASTM D2176-69	double folds	20			
Thermal						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x 10 ⁻⁵ /°F)	3.2	ISO 11359	(x 10 ⁻⁵ /°C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417/D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	347		°C	175
Heat Deflection Temp. by TMA at 1.8 MPa		°F	290	ISO 75 Modified	°C	145
Shrinkage at 302 °F (150 °C)	ASTM D1204	%	0.02%		%	0.02%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

UL Flammability Rating / Performance Levels

Thickness	Rating	HWI	HAI
>= 0.010" (0.250 mm) and < 0.015" (0.375 mm)	UL94V-0	1	0
> 0.015" (0.375 mm)	UL94V-0	0	0
CTI: 3			
File Number	E61257		

Manufacturing Specifications

Nominal Gauge Ranges 0.010-0.030" (0.250-0.750 mm)	Min./Max Limit of Nominal ± 5%
---	-----------------------------------



- 1 These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Advanced Materials, Specialty Film & Sheet representative or the GE Advanced Materials, Specialty Film & Sheet Quality Services Department. Reported values are based on 0.010" (0.250 mm) thickness unless otherwise noted.
- * Lexan is a trademark of General Electric Company.

GE Advanced Materials Specialty Film & Sheet

Property	ASTM Test Method	Units	Value	ISO Test Method	Units	Value
Physical						
Density	ASTM D792	slug/ft ³	2.6	ISO 1183	kg/m ³	1344
Water Absorption, 24 hrs.	ASTM D570	% change	0.28	ISO 62	% change	0.28
Surface Energy (1st surface / 2nd surface)	ASTM D5946-01	-	34/36			
Surface Tension (1st surface / 2nd surface)	Dyne Pens	Dyne	>44 / >44			
Optical						
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	7	ISO 2813	-	7
Electrical						
Dielectric Strength in oil, short time @ 72 °F (23 °C), 10 mils (0.25 mm)	ASTM D149-97a Method A	kV/mil	1.5	IEC 60243	kV/mm	59
Dielectric Constant @ 60 Hz	ASTM D150	-	2.9	IEC 60250	-	2.9
@ 1,000,000 Hz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor @ 60 Hz	ASTM D150	-	0.0026	IEC 60250	-	0.0026
@ 1,000,000 Hz	ASTM D150	-	0.0117	IEC 60250	-	0.0117
Volume Resistivity	ASTM D257	Ω-cm	1.00E+17	IEC 60093	Ω-cm	1.00E+17
Surface Resistivity	ASTM D257	Ω/square	1.00E+16	IEC 60093	Ω/square	1.00E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	64			

Europe:

GE Advanced Materials
Specialty Film & Sheet
Plasticslaan 1
PO Box 112
NL - 4600 AC Bergen op Zoom
The Netherlands
Tel. (31) (164) 292742
Fax. (31) (164) 291986

Americas:

GE Advanced Materials
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 7506

Pacific:

GE Advanced Materials
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
Tel. (86) 21 6288 1088
Fax. (86) 21 6288 0818

For more information call:
(800) 451-3147

Visit us online at:
www.geadvancedmaterials.com

©2004 General Electric Company
All Rights Reserved

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE GE ADVANCED MATERIALS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE ADVANCED MATERIALS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GE ADVANCED MATERIALS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, GE ADVANCED MATERIALS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of GE Advanced Materials' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE Advanced Materials' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE Advanced Materials' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE Advanced Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Trademark of General Electric Company.

