

LEXAN[®] T2F Film

Product Datasheet

DESCRIPTION

LEXAN[®] T2F (True-2-Form[™]) polycarbonate film is specifically designed and manufactured for three-dimensional, thermoformed and insert-mould-decorated applications that require tight graphics registration. It offers superior lay-flat qualities during printing and a much lower variation of graphics after forming than both standard polycarbonate films and polycarbonate/polyester blend films. Excellent forming characteristics mean greater part-to-part consistency for the processor and design freedom for the OEM. In many applications, it allows you to take advantage of vacuum forming without the associated graphics registration variation. LEXAN T2F film has a smooth surface on one side and super fine matte surface on the other offering the IMD part manufacturer new flexibility. In addition, the film offers the traditional benefits of polycarbonate films including clarity, color consistency, printability, and heat resistance.

Typical Property Values¹

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength						
@ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2506
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100-154
Gardner Impact Strength at 0.03 in. (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propogation	ASTM D1922	g/mil	30-55		g/mil	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010 inch (0.25 mm)	ASTM D2176-69	double folds	60			
0.020 inch (0.50 mm)	ASTM D2176-69	double folds	20			
Thermal						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x 10 ⁻⁵ /°F)	3.2	ISO 11359	(x 10 ⁻⁵ /°C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417/D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	312		°C	156
Heat Deflection Temp. by TMA at 1.8 MPa		°F	350	ISO 75 Modified	°C	175
Shrinkage at 302 °F (150 °C)	ASTM D1204	%	1.40%		%	1.40%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.007" (0.175 mm)	± 10%
0.010" (0.250 mm)	± 5%
0.015-0.020" (0.375-0.500 mm)	± 3%



1 These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Advanced Materials, Specialty Film & Sheet representative or the GE Advanced Materials, Specialty Film & Sheet Quality Services Department. Reported values are based on 0.010" (0.250 mm) thickness unless otherwise noted.
* LEXAN is a trademark of General Electric Company.

GE Advanced Materials Specialty Film & Sheet

Property	ASTM Test Method	Units	Value	ISO Test Method	Units	Value
Physical						
Density	ASTM D792	slug/ft ³	75	ISO 1183	kg/m ³	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Roughness (RMS)	ASME B46-1	-	x			
Surface Energy (1st surface / 2nd surface)	ASTM D5946-01	-	35/34			
Surface Tension (1st surface / 2nd surface)	Dyne Pens	Dyne	>44 / 38-40			
Optical						
Refractive Index @ 77 °F (25 °C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	88			
Yellowness Index	ASTM D1925	%	1.2			
Haze	ASTM D1003	%	95			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	8.5	ISO 2813	-	8.5

Gloss by Gauge: (ASTMD 523-85)

	Gauge	Angle	Matte	
	T2F	0.008" (0.200 mm)	85°	Minimum Maximum
0.010" (0.250 mm)		85°	Minimum Maximum	5 11
0.015" (0.375 mm)		85°	Minimum Maximum	6 15
0.020" (0.500 mm)		85°	Minimum Maximum	9 15



GE Advanced Materials Specialty Film & Sheet

Europe:
GE Advanced Materials
Specialty Film & Sheet
Plasticslaan 1
PO Box 112
NL - 4600 AC Bergen op Zoom
The Netherlands
Tel. +31 (164) 292742
Fax. +31 (164) 291986

Americas:
GE Advanced Materials
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. +1 (413) 448 7110
Fax. +1 (413) 448 7506

Pacific:
GE Advanced Materials
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
Tel. +86 21 6288 1088
Fax. +86 21 6288 0818

For more information call: (800) 451-3147

Visit us online at: www.geadvancedmaterials.com

©2005 General Electric Company
All Rights Reserved

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE GE ADVANCED MATERIALS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE ADVANCED MATERIALS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GE ADVANCED MATERIALS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, GE ADVANCED MATERIALS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of GE Advanced Materials' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE Advanced Materials' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE Advanced Materials' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE Advanced Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* LEXAN is a trademark of General Electric Company.

