



Melinex®

polyester film

MXTD229 Issue 1

Melinex® 725

Melinex® 725 is a sparkling optically clear knurled film with an adhesion promoting pre treatment on both surfaces. It is normally used in the Graphics industry where its' excellent clarity and printing/coating adhesion are utilised particularly when UV cured inks are used in multipass applications.

Melinex® 725 is available in thicknesses of 125, 175 and 250 micron.

TYPICAL VALUES OF PROPERTIES

Property	Test Methods	Unit	Value		
			Thickness mic		
General			125	175	250
Area Yield	--	m ² /kg	5.7	4.0	2.8
Relative Density (at 23°C)	ASTM D 1505-79 (modified to Melinex test method)	--	1.4		
Mechanical			MD*	TD**	
Minimum Tensile strength at break	ASTM D 882-83 (Strain rate 50%/min)	kgf/mm ²	17.5	17.5	
F5 (force to elongate 5% of gauge length)	ASTM D 882 (50% strain rate)	kgf/mm ²	10	10	
Optical			Thickness mic		
Haze	ASTM D1003-77 (Measured on Gardner Hazemeter)		125	175	250
			<2.0	<2.0	<2.5

Thermal

Upper Melt temperature	ASTM E794-85	°C	255 - 260
Coefficient of thermal expansion between 20 and 50°C	--	cm/cm°C	19 x 10 ⁻⁶ (MD) 16 x 10 ⁻⁶ (TD)
Shrinkage (after 5 mins at 190°C)	Melinex Method	%	1.0 (MD) 0.3(TD)

1µm = 1 micron = 0.001 mm approx. 4 gauge, *MD = Machine Direction, **TD = Transverse Direction

Enquiries should be addressed to:

DuPont Teijin Films (Luxembourg) SA
L-2984 Luxembourg
Telephone: +352 26164004
Fax No: +352 2616 5000

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont Teijin Films makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.



Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Teijin Films Medical Caution Statement", H-50102-DTF.

Melinex®, Kaladex®, Mylar®, Cronar®, Teonex® and Teijin® - Teton® are registered trademarks of DuPont Teijin Films. Only DuPont Teijin Films makes Melinex® brand, Kaladex® brand, Mylar® brand, Cronar® brand, Teonex® brand and Teijin® - Teton® brand films.

 DuPont Teijin Films

Melinex®

Only by DuPont Teijin Films