



Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

REFLECTAmark™ SG 450 WHITE REFLECTIVE V-344 90 PFW

GENERAL DESCRIPTION:

This is a white reflective film coated with a permanent pressure sensitive acrylic adhesive and backed with a two-side poly coated lay flat release liner.

PRODUCT DATA

VALUE

TEST METHOD

PHYSICAL PROPERTIES

Thickness mil (micron)	Film + Coating: 4.5 (51) +/- 15 % Adhesive: 0.9-1.0 (23-25) +/- 0.1 (3) Liner: 6.9 (175) +/- 10 %	ASTM D 3652
Dimensional Stability (%)	MD: 0.50 TD: 0.50	On Al panel at 160°F (71°C) for 24 hr.

ADHESION PROPERTIES**

Adhesion from	Average oz/in (N/m)	
Stainless Steel	46 (506)	ASTM D 903 (Modified for 72 hr dwell time)
Acrylic	57 (627)	
Glass	49 (539)	
Polypropylene	38 (418)	
Expected Shear (hours)	10	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (gm)	620	ASTM D 2979

** For guidance only, not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs. Sometime film rips during adhesion test.

EXPECTED EXTERIOR LIFE

Two years

SERVICE TEMPERATURE RANGE

-40°F to 176°F (-40°C to 80°C)

MINIMUM APPLICATION TEMPERATURE

50°F (10°C)

STORAGE STABILITY

Two years stored at 70°F (21°C) and 50% RH

* REFLECTAmark is a registered trademark of FLEXcon Company, Inc.

05/16/2006

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.