

# LEXAN™ HP01Wxx FILM

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN HP01Wxx graphic film is a virtually glare free film that uses SABIC's unique coatings technology allowing high light transmission for clear and sharp graphics. This high-performance coated film also offers very good chemical and abrasion resistance with excellent UV resistance. These performance capabilities, along with ease of processing, make HP01Wxx film a good choice for outdoor graphic applications such as warning labels, outdoor menu boards and gasoline pumps graphics.

### TYPICAL PROPERTY VALUES

PROPERTY	ASTM (ISO) TEST METHOD	UNITS USCS (SI)	HP01Wxx
<b>MECHANICAL</b>			
Tensile Strength @ Yield	ASTM D882 (ISO 527)	psi (MPa)	8800 (60)
Ultimate	ASTM D882 (ISO 527)	psi (MPa)	9000 (62)
<b>THERMAL</b>			
Vicat Softening Temperature, B	ASTM 1525	°F (°C)	320 (160)
Heat Deflection Temp. by TMA at 1.8 MPa	ISO 75 Modified	°F (°C)	290 (145)
Shrinkage at 302°F (150°C)	ASTM D1204	%	1.50%
<b>PHYSICAL</b>			
Density	ASTM D792 (ISO 1183)	slug/ft <sup>3</sup> (kg/m <sup>3</sup> )	2.3 (1200)
Pencil Hardness (coated surface)	ASTM D3363	-	HB-F
Taber Abrasion (CS10F, 500g, 50cycles)	ASTM D1044	delta Haze	0.2
<b>OPTICAL</b>			
Light Transmission	ASTM D1003	%	90
Yellowness Index	ASTM D1925	%	1
Haze	ASTM D1003	%	91
Gloss over Flat Black @ 60°	ASTM D523-60 (ISO 2813)	-	12
Gloss over Flat Black @ 85°	ASTM D523-60 (ISO 2813)	-	1
UV% Transmission at 350 nm	UV/Visual Spectroscopy	%	0.5
UV% Transmission at 360 nm	UV/Visual Spectroscopy	%	1.5
UV% Transmission at 370 nm	UV/Visual Spectroscopy	%	8

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.  
Reported Values are based on 0.030" (0.750 mm) Thickness unless otherwise noted.

™ Trademark of SABIC.

## MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.010" (0.250 mm)	- 10%/+20%
0.015" (0.375 mm)	- 5%/+12%
0.020" (0.500 mm)	-5%/+10%
0.030" (0.750 mm)	-8%/+8.5%

## UV RESISTANCE

LEXAN™ HP01Wxx film utilizes a proprietary coating technology developed by SABIC. This special coating resists yellowing and hazing. Yellowness index change of less than 3.0 at 1000 hours of QUV testing and less than 2.0 at 1000 hours of Xenon Arc testing make LEXAN™ HP01Wxx film a candidate for demanding outdoor applications.

## TABER ABRASION RESISTANCE (ASTM D1044) LEXAN HP01Wxx GRAPHIC FILM

CONDITION CS10F WHEEL, 500 GRAMS Cycles	HP01Wxx % Change in Haze by ASTM D1003
25	0.2%
50	0%
100	-0.3%
200	-0.4%

## CHEMICAL RESISTANCE

CHEMICAL	RESULTS†
<b>One Hour Continuous Surface Contact at 73° F</b>	
Acetone	Failed
MEK	Failed
Toluene	Failed
Methylene Chloride	Failed
Isopropyl Alcohol	Passed
Cyclohexanone	Passed
Ethyl Acetate	Failed
Xylene	Passed
40% NaOH	Passed
Concentrated HCl	Passed
Gasoline (Regular)	Passed
Gasoline (Unleaded)	Passed
Butyl Cellosolve	Passed

## CHEMICAL RESISTANCE

### 24 HOUR CONTINUOUS SURFACE CONTACT AT 120°F

Coffee	Passed
Top Job <sup>‡</sup>	Passed
Fantastik <sup>##</sup>	Passed
Formula 409 <sup>#</sup>	Passed
Windex w/ Ammonia D <sup>###</sup>	Passed
Wisk <sup>¶</sup>	Passed
Downy <sup>#</sup>	Passed
Spray N Wash <sup>##</sup>	Passed
Clorox <sup>*</sup>	Passed
Mustard	Passed
Mr. Clean <sup>#</sup>	Passed
Ketchup	Passed
Tea	Passed
Tomato Juice	Passed
Lemon Juice	Passed
Grape Juice	Passed
Vinegar	Passed
Milk	Passed

- † Failure constitutes any of the following: non-removable stain or cloudiness, blistering, delamination, or cracking of the coating or failure to pass crosshatch tape adhesion.
- ¶ Wisk is a registered trademark of Lever Brothers Company
- # Formula 409 and Clorox are registered trademarks of the Clorox Company
- # Top Job, Downy, and Mr. Clean are registered trademarks of Procter & Gamble
- ## Fantastik and Spray 'N Wash are registered trademarks of Texize, Division of Norton Norwich Products, Inc.
- ### Windex w/Ammonia D is a registered trademark of Drackett Products Company



## CONTACT US:

### SABIC CORPORATE HQ

PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E [info@sabic.com](mailto:info@sabic.com)

### AMERICAS

SABIC  
Functional Forms  
2500 City West Boulevard  
Suite 100  
Houston, TX 77042  
USA  
Toll-free (800) 323 3783  
F (888) 443 2033  
E [spinside.sales@sabic.com](mailto:spinside.sales@sabic.com)

### EUROPE

SABIC  
Functional Forms  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293684  
F +31 (0)164 292272  
E [ff.info@sabic.com](mailto:ff.info@sabic.com)

### PACIFIC

SABIC  
Functional Forms  
2550 Xiupu Road  
Pudong  
201319 Shanghai  
China  
T +86 21 3222 4500  
F +86 21 6289 8998

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with <sup>TM</sup> are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.