



CADILLAC
PLASTIC LIMITED

For more information and to order, please contact:

www.cadillacplastic.co.uk
info@cadcouk.com
01793 648500

Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

FLEX-Vu® OL 500 CLEAR VELVET L-29 142 POLY C-9

GENERAL DESCRIPTION:

This is a clear velvet embossed polycarbonate film coated with a clear over-laminating pressure sensitive acrylic adhesive and backed with an ultra smooth clear polyester release liner.

UL RECOGNITION:

This product is UL recognized for indoor use with occasional exposure to lubricating oil and water. For further information, please reference FLEXcon's UL file No MH10170 (N) or contact your FLEXcon Representative.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES		
Thickness (micron)	Film: 125 +/- 10 % Adhesive: 36-38 +/- 3 Liner: 36 +/- 10 %	ASTM D 3652
Dimensional Stability (%)	No shrinkage observed	On Al panel at 70°C for 24 hr.

ADHESION PROPERTIES**

Adhesion from (N/m)	Average	
Stainless Steel	979	FTM 1 (Modified for 72 hr dwell time)
Acrylic	1056	
Glass	1012	
Expected Shear (hours)	100 +	FTM 8
Tack (gm/sq cm)	670	ASTM D 2979

** For guidance only

This data is based on limited test results due to the custom nature of this product, not to be used for setting specifications.

EXPECTED EXTERIOR LIFE	Indoor use only
SERVICE TEMPERATURE RANGE	-40°C to 100°C
MINIMUM APPLICATION TEMPERATURE	10°C
STORAGE STABILITY	One year stored at 21°C and 50% RH

* FLEX-Vu is a registered trademark of FLEXcon Company, Inc.

05/01/2006

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.