



For more information and to order, please contact:

www.cadillacplastic.co.uk
info@cadcouk.com
01793 648500

Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

SEETHRU-SIGN™ White/Black Flex
STSWBF

GENERAL DESCRIPTION:

This is a perforated white/black flexible vinyl film coated with a removable pressure sensitive acrylic adhesive and backed with a two side poly coated lay flat release liner.

PRODUCT DATA	VALUE	TEST METHOD
--------------	-------	-------------

PHYSICAL PROPERTIES

Thickness (micron)	Film:	183	+/- 15 %	ASTM D 3652
	Adhesive:	23-25	+/- 3	
	Liner:	170	+/- 10 %	

Dimensional Stability (%)	MD:	0.40	On Al panel at 70°C for 24 hr.
	TD:	0.40	

ADHESION PROPERTIES**

Adhesion from (N/m)	Average	
Stainless Steel	242	FTM 1 (Modified for 72 hr dwell time)
Acrylic	264	
Glass	220	
Expected Shear (hours)	25	FTM 8
Tack (gm/sq cm)	130	ASTM D 2979

** For guidance only

This data is based on limited test results due to the custom nature of this product, not to be used for setting specifications.

EXPECTED EXTERIOR LIFE Two years

SERVICE TEMPERATURE RANGE -40°C to 50°C

MINIMUM APPLICATION TEMPERATURE 10°C

STORAGE STABILITY Two years stored at 21°C and 50% RH

* SEETHRU-SIGN is a trademark of FLEXcon Company, Inc.

15/08/2002

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.