

Lexan* 8B35VE Film

Product Datasheet

Description

Lexan* 8B35VE Film is a transparent polycarbonate film, velvet on one side and very fine matte on the other, that offers excellent clarity, high heat resistance, and superior dimensional stability in all thicknesses. Lexan 8B35VE Film can be printed using traditional solvent-based inks as well as IR and UV curing inks. It offers ease of processing for thermoforming, hydroforming, embossing, diecutting and bending.

Typical Property Values ♦

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength	ASTM D882	psi	8500	ISO 527	MPa	62
@ Yield	ASTM D882	psi	9000	ISO 527	MPa	65
Ultimate	ASTM D882	psi	300000	ISO 527	MPa	2506
Tensile Modulus	ASTM D882	%	100-160	ISO 527	%	100-154
Tensile Elongation at Break	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Gardner Impact Strength at 0.03 in. (0.75 mm)						
Tear Strength	ASTM D1004	lb/mil	1.4 - 1.8		kN/m	245
Initiation	ASTM D1922	g/mil	30 - 55		g/mil	10-20
Propogation	ASTM D3763	ft-lb	9		J	12
Puncture Resistance (Dynatup)						
Fold Endurance (MIT)						130
0.010 inch (0.25 mm)	ASTM D2176-69	double folds	60			35
0.020 inch (0.50 mm)	ASTM D2176-69	double folds	20			
Thermal						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft2/°F/in	1.35		W/m°K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x 10-5 / °F)	3.2	ISO 11359	(x 10-5 / °C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417/D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	312		°C	156
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75 Modified	°C	145
Shrinkage at 302°F (150°C)	ASTM D1204	%	0.80%		%	0.80%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135
Physical						
Density	ASTM D792	slug/ft3	2.4	ISO 1183	kg/m ³	1230
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Roughness (RMS)	ASME B46-1	-	6.3 (VFM) / 34 (V)	-	-	-
Surface Roughness (Ra)	-	-	-	DIN4768	µm	0.5-1.5 [VFM] 2.6-5.2[V]
Surface Tension (1 st surface/2 nd surface)	Dyne Pens	Dyne	>34 / >34	-	-	-
Optical						
Refractive Index @77°F (25°C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	86			
Yellowness Index	ASTM D1925	%	1.9			
Haze	ASTM D1003	%	100			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	%	2.8-13.2 (VFM) 2.0- 9.8 (V)	ISO 2813	%	2.8-13.2 [VFM] 2.0- 9.8 [V]

♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are Based on 0.010" (0.250 mm) thickness unless otherwise noted.

* Trademark of SABIC Innovative Plastics IP BV

UL flammability rating / performance levels

Thickness	Rating
0.005-0.020" (0.125-0.500 mm)	UL94V-2

Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.005-0.010" (0.125-0.250 mm)	± 8%
0.015-0.020" (0.375-0.500 mm)	± 5%



* Trademark of SABIC Innovative Plastics IP BV

Americas:
SABIC Innovative Plastics
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 5573

Europe:
SABIC Innovative Plastics
Specialty Film & Sheet
Plasticslaan 1
NL - 4612 PX Bergen op Zoom
The Netherlands
Tel. (31) (164) 292911
Fax. (31) (164) 292940

Pacific:
SABIC Innovative Plastics
Specialty Film & Sheet
1468 Nanjin Road (W)
26th Floor, United Plaza
200040 Shanghai, China
Tel. (86) 21 3222 4500
Fax. (86) 21 6289 8998

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP BV