

# ULTEM™ 1000B NATURAL FILM

## (75 µm - 175 µm)

### PRODUCT DATASHEET

#### DESCRIPTION

ULTEM™ 1000B film is a high performance thermoplastic Polyetherimide material. The combination of high temperature resistance, flame resistance, low moisture absorption and excellent dielectric properties makes ULTEM film a good candidate for a broad range of electrical and electronic applications. ULTEM film products are thermo-formable and can be heat-sealed to a wide variety of materials.

#### TYPICAL PROPERTY VALUES ◆

PROPERTY	TEST METHOD	UNITS	VALUE
<b>Mechanical</b>			
Tensile Modulus	ISO R527	MPa	3000
Tensile Strength @ Yield	ISO R527	MPa	100
Tensile Elongation at @ Yield	ISO R527	%	6.5
Tensile Strength @ Break	ISO R527	%	60
Tear Strength Initiation @75 µm	ASTM D1004	N/mm	360
Tear Strength Propagation @75 µm	ASTM D1938	N/mm	3.5
<b>Thermal</b>			
Coefficient of Thermal Expansion	IPC-TM-650	ppm/°C	52
Shrinkage @ 170°C EXT. DIR.	IPC-TM-650	%	0.33
Shrinkage @ 170°C CROSS. DIR.	IPC-TM-650	%	0.24
Glass Transition Temperature	DMA	°C	217
Thermal Conductivity	ASTM C177	W/m°C	0.22
<b>Physical</b>			
Specific Gravity	ISO 1183	g/cc	1.27
Water Absorption, immersion, 23°C, 24 hr	ASTM D570	%	1.25
Water Absorption, 50%RH, 23°C, 24 hr.	ASTM D570	%	0.48
<b>Electrical</b>			
Dielectric Strength @ 125 µm oil	ASTM D149	Volts/mil	3,650
Dielectric Constant	IPC-TM-650		3.2
Dissipation Factor	IPC-TM-650		0.005
Volume Resistivity	ASTM D257	M 'Ω-cm	2.5 x 10 <sup>15</sup>
Surface Resistivity	ASTM D257	M 'Ω	1.9 x 10 <sup>16</sup>
<b>Flammability</b>			
UL listing film: <a href="#">E45329</a>			

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.

™ Trademark of SABIC.

## PRODUCT AVAILABILITY

Standard gauges	: 75 µm (0,003") +/-5% - 175 µm (0,020") +/-5%
Standard roll width	: 1270 mm (50")
Texture	: Smooth / fine matte
Color code	: 1000
Color	: Natural amber

## CONTACT US:

### SABIC CORPORATE HQ

PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E [info@sabic.com](mailto:info@sabic.com)

### AMERICAS

SABIC  
Functional Forms  
2500 CityWest Boulevard  
Suite 100  
Houston, TX 77042  
USA  
Toll-free (800) 323 3783  
F (888) 443 2033  
E [spinside.sales@sabic.com](mailto:spinside.sales@sabic.com)

### EUROPE

SABIC  
Functional Forms  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293684  
F +31 (0)164 293272  
E [ff.info@sabic.com](mailto:ff.info@sabic.com)

### PACIFIC

SABIC  
Functional Forms  
2550 Xiupu Road  
Pudong  
201319 Shanghai  
China  
T +86 21 3222 4500  
F +86 21 6289 8998  
E [ff.info@sabic.com](mailto:ff.info@sabic.com)

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with <sup>TM</sup> are trademarks of SABIC or affiliates.  
© Copyright 2021. All rights reserved.

<sup>1</sup> Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

