

## DuPont™ Tyvek® 1025D

### Product Properties—Metric Units

**Product Features:**  
**Antistatic Treatment**  
**Corona Treated**

#### Specification Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1025D
Basis Weight	DIN EN ISO 536 (96) <sup>1</sup>	g/m <sup>2</sup>	42.5 [40.5–45.0]
Delamination	ASTM D2724-03 <sup>3</sup>	N	1.00 [0.70–1.4]

Notes: All specification properties are typical values based on mill roll averages, with samples taken uniformly across the sheet.

1. Modified for size: 100 cm<sup>2</sup>

3. Modified for: length of delamination = 116 mm, width 25.4 mm, speed = 127 mm/min and clamp distance = 60 mm

#### Miscellaneous Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1025D
Opacity	ISO 2471 (98) <sup>4</sup>	%	96
Elmendorf Tear, MD	DIN EN 21974 (94)	N	6.0
Elmendorf Tear, CD	DIN EN 21974 (94)	N	5.7
Tensile Strength, MD	DIN EN ISO 1924-2 (08) <sup>5</sup>	N	94
Tensile Strength, CD	DIN EN ISO 1924-2 (08) <sup>5</sup>	N	90
Elongation, MD	DIN EN ISO 1924-2 (08)	%	11–21
Elongation, CD	DIN EN ISO 1924-2 (08)	%	15–25
Mullenburst	ISO 2758 (01)	kPa	550
Thickness	DIN EN ISO 534 (05) <sup>2</sup>	µm	140

Notes: Miscellaneous properties are typical values based on mill roll averages, unless otherwise noted but are not warranted in any way, expressed or implied. Miscellaneous properties are not controlled in the process and are subject to normal process drift.

MD = machine direction; CD = cross direction.

2. Surface 2 cm<sup>2</sup>, pressure 50kPa

4. Modified for: backing standards, measuring area, and illumination = wide area.

5. Modified for: speed = 100 mm/min and gauge length = 127 mm; width 25.4 mm

For more information, connect with us at: [www.graphics.dupont.com](http://www.graphics.dupont.com)

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

©2019 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

## DuPont™ Tyvek® 1025D

### Product Properties—English Units

**Product Features:**  
**Antistatic Treatment**  
**Corona Treated**

#### Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1025D
Basis Weight	DIN EN ISO 536 (96) <sup>1</sup>	oz/yd <sup>2</sup>	1.25 [1.19–1.33]
Delamination	ASTM D2724-03 <sup>3</sup>	lb <sub>f</sub>	0.225 [0.157–0.315]

Notes: All specification properties are typical values based on mill roll averages, with samples taken uniformly across the sheet.

1. Modified for size: 100 cm<sup>2</sup>

3. Modified for: length of delamination = 116 mm, width 25.4 mm, speed = 127 mm/min and clamp distance = 60 mm

#### Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1025D
Opacity	ISO 2471 (98) <sup>4</sup>	%	96
Elmendorf Tear, MD	DIN EN 21974 (94)	lb <sub>f</sub>	1.35
Elmendorf Tear, CD	DIN EN 21974 (94)	lb <sub>f</sub>	1.28
Tensile Strength, MD	DIN EN ISO 1924-2 (08) <sup>5</sup>	lb <sub>f</sub>	21.13
Tensile Strength, CD	DIN EN ISO 1924-2 (08) <sup>5</sup>	lb <sub>f</sub>	20.23
Elongation, MD	DIN EN ISO 1924-2 (08)	%	11–21
Elongation, CD	DIN EN ISO 1924-2 (08)	%	15–25
Mullenburst	ISO 2758 (01)	psi	79.77
Thickness	DIN EN ISO 534 (05) <sup>2</sup>	mils	5.5

Notes: Miscellaneous properties are typical values based on mill roll averages, unless otherwise noted but are not warranted in any way, expressed or implied. Miscellaneous properties are not controlled in the process and are subject to normal process drift.

MD = machine direction; CD = cross direction.

2. Surface 2 cm<sup>2</sup>, pressure 50kPa

4. Modified for: backing standards, measuring area, and illumination = wide area.

5. Modified for: speed = 100 mm/min and gauge length = 127 mm; width 25.4 mm

For more information, connect with us at: [www.graphics.dupont.com](http://www.graphics.dupont.com)

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

©2019 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.