



# Melinex<sup>®</sup>

polyester film

## Melinex<sup>®</sup> 401

### Product Description

Melinex<sup>®</sup> 401 is a sparkling clear film with good handling qualities. Melinex<sup>®</sup> 401 is supplied in knurled reel form and is currently available at 50, 75 and 100 micron.

### Typical Applications

Melinex<sup>®</sup> 401 is specially treated to give a slippery surface on one side, is suitable for applications where very high transparency is important.

### General Information

As per Article 3(3) of the REACH regulation (EC) No 1907/2006 Melinex<sup>®</sup> 401 film is classified as an article. There are no substances intended to be released from the above film under normal, reasonably foreseeable conditions of use, as defined by Article 7(1).

### Food Contact Advice

Melinex<sup>®</sup> 401 has not been assessed against Food Contact Legislation

### Film Properties

Property	Unit	Typical Values			Test Method
		50	75	100	
<b>General</b>					
Thickness	micron	50	75	100	DTF Method
Area Yield	m <sup>2</sup> /kg	14.4	9.6	7.2	DTF Method
Relative Density (23°C)		1.4			Based on ASTM D1505-79
<b>Mechanical</b>					
Tensile Strength at Break	kgf/mm <sup>2</sup>	MD 18.5	TD 24		Based on ASTM D882-83
Elongation at Break	%	MD 150	TD 100		Based on ASTM D882-83
Slip (coefficient of static friction)	treated to untreated	0.6			Based on ASTM D1894-78
F5	kgf/mm <sup>2</sup>	MD 10.5	TD 10.5		Based on ASTM D882-83
<b>Optical</b>					
Haze	%	<0.6	<1	<1	Based on ASTM D1003-77
<b>Thermal</b>					
Upper Melt Temperature	°C	255-260			Based on ASTM E794-85
Coefficient of thermal expansion	ppm/K	19			Based on ASTM E831-06 between 20-50°C
Shrinkage (at 150°C/30 mins)	%	MD 1	TD 0.7		Based on ASTM D1204-78

## Disposal Advice

Disposal of Melinex® 401 does not present special disposal problems. Where waste occurs in a clean, uncontaminated form it can be recycled. In most circumstances, once Melinex® 401 has been laminated, coated, printed or metallised, incineration with Energy Recovery is the most environmentally efficient recovery route. Melinex® 401 can also be burned in an incinerator with normal refuse or can be buried as a relatively inert material in a landfill. The disposal method should comply with appropriate local and country regulations.

Date of Last Revision: 21 Aug 2017

DuPont Teijin Films Contacts	
<b>Continental Europe</b> DuPont Teijin Films (Luxembourg) SA BP-1681 L-1016 Luxembourg Telephone +352 2616 4004 Fax +352 2616 5000	<b>United Kingdom</b> DuPont Teijin Films (UK) Ltd The Wilton Centre Redcar TS10 4RF England, UK Telephone +44 (0) 1642 572000 Fax +44 (0) 1642 572075
<a href="http://www.dupontteijinfilms.com">http://www.dupontteijinfilms.com</a>	e-mail: <a href="mailto:europa.films@ubr.dupont.com">europa.films@ubr.dupont.com</a> e-mail: <a href="mailto:packaging.films@ubr.dupont.com">packaging.films@ubr.dupont.com</a>

The information provided in this Product Information Note corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont Teijin Films cannot anticipate all variations in actual end-use conditions DuPont Teijin Films makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Teijin Films Medical Caution Statement", H-50102-3-DTF and H-50103-3-DTF.

Copyright © 2017 DuPont Teijin Films. Melinex® and Mylar® are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teonex® is registered trademark of Teijin Films Solutions Limited and licensed to DuPont Teijin Films U.S. Limited Partnership.

©2017 DuPont Teijin Films. All rights reserved